

Troldtekt® A2 acoustic panels

Data sheet

THE PRODUCT – TROLDTEKT A2

Troldtekt A2 are cement-bonded wood wool panels made from wood and cement. The product consists of wood (spruce) which is shredded into wood wool and mixed with cement.

We offer PEFC™-certified or FSC®-certified Norway spruce (FSC® C115450). Both certifications guarantee that the wood comes from responsible forestry operations.

Troldtekt can be surface-treated, but is often used unprocessed (natural wood). Due to the nature of the material, colour variations may occur. Among the factors affecting colour variations are water/cement ratio, water content of the wood, drying rate, steam curing and curing moisture.

PRODUCT STANDARDS, LABELLING AND CERTIFICATES

CE marking

CE marking of building materials is required by law in the EU. The CE mark indicates that the building material in question can be legally sold and is in correspondence with the product standard to which the mark refers. Troldtekt products are CE marked and in addition to the marking, we state:

Name of the producer:
Troldtekt A/S

Certificate numbers:
0615 – CPD – 222958G
0615 – CPD – 804474G

Product standard number:
EN 13168 and EN 13964

Declaration:
See product data on page 2

Light reflection

Light reflection for different types of Troldtekt panels (measured by DELTA Light and Optics):

| | |
|-------------------------|-------|
| Troldtekt white 101 | 70.8% |
| Troldtekt light natural | 55.2% |

USE AND MAINTENANCE

Troldtekt panels usually require no subsequent care. However, we recommend regular cleaning along with other surfaces – and otherwise as required. Light cleaning of the panels is easy using a vacuum cleaner with a brush nozzle. Should vacuum-cleaning prove insufficient, you

can wipe the panels using a lightly damp cloth. If you subsequently want to paint the Troldtekt ceiling, you can use a long-haired paint roller or a hand sprayer. Water-based paint will not reduce the sound-absorbing performance of the panels.

RECYCLING

The entire range of Troldtekt cement-bonded wood wool panels are Cradle to Cradle-certified in the silver category. Consequently, we have complete documentation of the substances in the products, and documentation that the

products can be composted and safely returned to nature as a soil conditioner. The cement in Troldtekt's acoustic panels boosts oxygen levels during the composting process, while the wood adds organic material to the compost.

TOLERANCES

It is important to note that Troldtekt is a natural material and the very nature of the material composition – wood wool and cement – will incur small variations in the panels. Panel dimensions and weights

remain inside the tolerance indicated at 23 +/- 2 °C and 50 +/- 5 % relative humidity. However, inappropriate storage and lack of acclimatisation could alter panel dimension and weight. It is therefore

important that you observe the installation, storage and acclimatisation instructions carefully.

PRODUCT DATA

The table below indicates the tolerances declared by us in accordance with EN 13168, the standard for cement-bonded wood wool and double-layer panels with cement-bonded wood wool, and EN 13964, the standard for suspended ceilings.

Properties:

| DIMENSIONS | |
|----------------|---------------|
| Width (mm) | 600 |
| Length (mm) | 600/1200/2400 |
| Thickness (mm) | 25 35 |

| Weight (kg/m ²) | |
|-----------------------------|-----------|
| Fine | 12,4 14,3 |
| Ultrafine | 12,7 14,6 |
| Extreme fine | 12,8 14,8 |

| TOLERANCES | |
|-----------------------|-----------------------|
| Length (mm) | ≥ 1.250 : ±2.0 |
| | ≤ 1.250 : ±1.0 |
| Width (mm) | ±1.0 |
| Thickness (mm) | Length ≥ 1.250 : ±2.0 |
| | Length ≤ 1.250 : ±1.0 |
| % by weight | ±10 |
| Perpendicularity (mm) | ±≤2 |
| Planeness (mm) | ±≤3 |

| HEAT | |
|--------------------|-------|
| Lambda value W/m·K | 0.088 |

| FIRE | |
|------------------|----------|
| Reaction to fire | A2/s1/d0 |

| SUBSTANCES | |
|--------------|-------|
| Chloride % | ≤0.06 |
| Formaldehyde | E1 |

| STANDARD | |
|-----------------------------|----------------------|
| Declared in accordance with | EN 13168 EN 13964 |

Troldtekt A/S
Sletvej 2A
DK-8310 Tranbjerg J
Tel. +45 8747 8100
Fax +45 8747 8111
info@troldtekt.dk
www.troldtekt.com